



ESL ELECTROSCIENCE

CERAMIC TAPES &
THICK-FILM MATERIALS

416 EAST CHURCH ROAD
KING OF PRUSSIA, PA 19406-2625 USA

T: 610.272.8000
F: 610.272.6759

www.electroscience.com

FUGITIVE PASTE

4441

Cadmium-free, Lead-free* for SOFC, other Fuel Cells, and HTCC Sensors

ESL 4441 is a FUGITIVE paste composition that burns out cleanly at 850°C. This paste can be used to form channels in multilayer tape structures or, when mixed with other inks, to increase porosity. It is a screen-printable thick-film paste. The rheology of the material can be modified on a custom basis for use with alternative deposition techniques.

PASTE DATA

RHEOLOGY:	Thixotropic, screen printable paste
VISCOSITY: (Brookfield HBT, cone/plate, 38.4 sec ⁻¹ at 25.0°C ± 0.5°C)	70 ± 15 Pa•s
COLOR:	Black
Residue: (850°C, 30 min. in air)	<0.1%

PROCESSING

LEVELING TIME: (25°C)	5-10 minutes
DRYING AT 125°C:	10-15 minutes
SHELF LIFE: (at 25°C)	6 months
COMPATIBILITY:	ESL HTCC tapes such as 42000 & 44000 Series

4441 1104-new

ESL Affiliates

ESL China • Rm#1707, Tower A • City Center of Shanghai • 100 Zunyi Road • Shanghai, China 200051 Tel: (011-86)-21-62370336 • Fax: (011-86)-21-62370338 • eslchina@eslshanghai.net

ESL Europe • 8 Commercial Road • Reading, Berkshire, England RG2 0QZ • Tel: (011-44)-118-918-2400 • Fax: (011-44)-118-986-7331 • Sales@ESLEurope.co.uk

ESL Nippon • Sukegawa Bldg • 6th floor • 3-4 Yanagibashi 1-chome • Taito-ku • Tokyo 111, Japan • Tel: (011-81)-3-3864-8521 • Fax: (011-81)-3-3864-9270 • Sales@ESL-Nippon.co.jp

See Caution and Disclaimer on other side.

PAGE BLANK

4441 1104-new

***Complies with RoHS, ELV, WEEE and CHIP 3 EC directives.**

CAUTION: Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapors emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

DISCLAIMER: The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. Electro-Science assumes no liability for any injury, loss, or damage, direct or consequential arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make their own tests to determine the suitability thereof for their particular use, before using it. User assumes all risk and liability whatsoever in connection with their intended use. Electro-Science's only obligation shall be to replace such quantity of the product proved defective.
